

| | |
|------------------------------|--|
| FEATURES | CAMEL Matt Lacquer is formulated from high-quality Nitro-Cellulose. It is suitable for the interior wood application. Paint film is fast-drying, gives high performance for decoration, high endurance quality, Matt film and highly adhesive with real wood and plywood with texture/grain. Non-mercuric and non-leaded paints. |
| TECHNICAL INFORMATION | |
| Type | Nitro-Cellulose Lacquer |
| Color | Clear |
| Film appearance | Matt |
| Pack size | 5, 1 and 1/4 Gallon |
| Solid by volumn | 25±2 |
| Solid by weight | 37±2% |
| Flash point | 4 |
| Specific gravity | 0.90-1.00 |
| Wet film thickness | 80-100 Micron |
| Dry film thickness | 20-25 Micron |
| Theoretical coverage | 35-40 Sq.m./coat/gallon |
| Touch dry (25-30°C) | 4-6 Minutes |
| Recoat dry (25-30°C) | 25-30 Minutes |
| Full cure (25-30°C) | 2-3 Hours |
| APPLICATION | |
| Tools | Brush and Spray gun |
| Dilution (%) | Thinner 100-200% |
| APPLICATION SYSTEM | |
| Surface Preparation | |
| Old surfaces | Chalky surfaces or loose material must be removed by stiff brush. The surfaces must be clean and free of dirt, wax, salt, old paint and other contaminants |
| New surfaces | Use abrasive paper to sand the wood surface until smooth, fill all wood crack and hole by filler. Sand again until the smooth surface is obtained. The surfaces must be clean and free of dirt, grease, oil, wax, salt and other contaminants. |
| Coating system | |
| Primer | Apply Clear Lacquer 2-3 coats |
| Topcoat | Apply 2-3 coats of CAMEL Lacquer (Matt) |
| | Flash off time between coat 5-10 minutes |
| HANDLING AND STORAGE | Keep the containers in a dry, cool, well ventilated space and away from heat. Containers must be kept tightly closed. |
| HEALTH AND SAFETY | Use under well ventilated conditions. Avoid skin contact. |